

# CE 221

**CE 221 is a high-performance material with excellent strength, stiffness, and temperature resistance.**

<b>Tensile Properties</b> ASTM D638, Type V, 1 mm/min	<b>Metric</b>	<b>US</b>
Tensile Modulus	3900 MPa	570 ksi
Ultimate Tensile Strength	85 MPa	12 ksi
Elongation at Break	3%	3%

<b>Flexural Properties</b> ASTM D790-B	<b>Metric</b>	<b>US</b>
Flexural Stress at 5% strain	130 MPa	19 ksi
Flexural Modulus (Chord, 0.5-1%)	3800 MPa	550 ksi

<b>Impact Properties</b>	<b>Metric</b>	<b>US</b>
Notched Charpy (Machined Notch), ISO 179-1/1eA	1.2 kJ/m <sup>2</sup>	0.6 ft-lb/in <sup>2</sup>
Notched Izod (Machined Notch), ASTM D256	15 J/m	0.3 ft-lb/in
Unnotched Izod, ASTM D4812	290 J/m	5 ft-lb/in

<b>Thermal Properties</b>	<b>Metric</b>	<b>US</b>
Heat Deflection Temperature at 0.455 MPa/66 psi, ASTM D648	230 °C	450 °F
Heat Deflection Temperature at 1.82 MPa/264 psi, ASTM D648	200 °C	390 °F
Coefficient of Thermal Expansion (-60, 100 °C), ASTM E831	50 ppm/°C	30 ppm/°F
Coefficient of Thermal Expansion (100, 180 °C), ASTM E831	90 ppm/°C	50 ppm/°F
Coefficient of Thermal Expansion (180, 200 °C), ASTM E831	150 ppm/°C	80 ppm/°F
Heat Capacity, 23 °C, ASTM E1269	1.2 J/g-°C	0.3 BTU/lb-°F
Thermal Conductivity, ASTM C518	0.17 W/m-k	0.1 BTU/hr-ft-°F

The information in this document includes values derived from printing various parts, reflects an approximation of the mean value of a range of values, and is intended for reference and comparison purposes only. This information should not be used for testing, design specification or quality control purposes. End-use material performance can be impacted by, but not limited to, design, processing, color treatment, operating and end-use conditions, test conditions, etc. Actual values will vary with build conditions. In addition, product specifications are subject to change without notice.

This information and Carbon's technical advice are given to you in good faith but without warranty. The application, use and processing of these and other Carbon products by you are beyond Carbon's control and, therefore, entirely your own responsibility. Carbon products are only to be used by you, subject to the terms of the written agreement by and between you and Carbon.

You are responsible for determining that the Carbon material is safe, lawful, and technically suitable for the intended application, as well as for identifying the proper disposal (or recycling) method consistent with applicable environmental laws and regulations. CARBON MAKES NO WARRANTIES OF ANY KIND, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR USE, OR NON-INFRINGEMENT. Further, it is expressly understood and agreed that you assume and hereby expressly release Carbon from all liability, in tort, contract or otherwise, incurred in connection with the use of Carbon products, technical assistance and information. No license with respect to any intellectual property is implied.

Parts were processed using an M series printer and washed using 50/50 (v/v) propylene glycol/isopropyl alcohol solvent.

<b>Dielectric/Electric Properties</b>	
Dielectric Strength, ASTM D149	22 kV/mm
Dielectric Constant, ASTM D150	3.1
Dissipation Factor, ASTM D150	0.05
Volume Resistivity, ASTM D257	2.2 E+14 ohm-cm

<b>General Properties</b>	
Hardness, ASTM D2240	92, Shore D
Density, ASTM D792	1.20 g/cm <sup>3</sup>
Density (liquid resin)	1.15 g/cm <sup>3</sup>
Taber Abrasion, ASTM D4060, CS-17, 1 kg, 100% vacuum	40 mg/ 1000 cycles
Water Absorption, Short Term (24 hours) ASTM D570	< 0.5%
Water Absorption, Long Term (14 days) ASTM D570	< 1%

The information in this document includes values derived from printing various parts, reflects an approximation of the mean value of a range of values, and is intended for reference and comparison purposes only. This information should not be used for testing, design specification or quality control purposes. End-use material performance can be impacted by, but not limited to, design, processing, color treatment, operating and end-use conditions, test conditions, etc. Actual values will vary with build conditions. In addition, product specifications are subject to change without notice.

This information and Carbon's technical advice are given to you in good faith but without warranty. The application, use and processing of these and other Carbon products by you are beyond Carbon's control and, therefore, entirely your own responsibility. Carbon products are only to be used by you, subject to the terms of the written agreement by and between you and Carbon.

You are responsible for determining that the Carbon material is safe, lawful, and technically suitable for the intended application, as well as for identifying the proper disposal (or recycling) method consistent with applicable environmental laws and regulations. CARBON MAKES NO WARRANTIES OF ANY KIND, EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR USE, OR NON-INFRINGEMENT. Further, it is expressly understood and agreed that you assume and hereby expressly release Carbon from all liability, in tort, contract or otherwise, incurred in connection with the use of Carbon products, technical assistance and information. No license with respect to any intellectual property is implied.

Parts were processed using an M series printer and washed using 50/50 (v/v) propylene glycol/isopropyl alcohol solvent.


# CE 221

## Extended TDS

# CE 221 Mechanical Properties

## Representative Tensile Curve

ASTM D638, Type V, 1 mm/min




# CE 221 Chemical Compatibility

	Mass Gain* (%)
<b>Household Chemicals</b>	
Bleach (NaClO, 5%)	< 5%
Sanitizer (NH <sub>2</sub> Cl, 10%)	< 5%
Distilled Water	< 5%
Sunscreen (Banana Boat, SPF 50)	< 5%
Detergent (Tide, Original)	< 5%
Windex Powerized Formula	< 5%
Hydrogen Peroxide (30%)	< 5%
Ethanol (95%)	< 5%
<b>Industrial Fluids</b>	
Engine Oil (Havoline SAE 5W-30)	< 5%
Brake Fluid (Castrol DOT-4)	< 5%
Airplane Deicing Fluid (Type I Ethylene Glycol)	< 5%
Airplane Deicing Fluid (Type I Propylene Glycol)	< 5%
Airplane Deicing Fluid (Type IV Ethylene Glycol)	< 5%
Airplane Deicing Fluid (Type IV Propylene Glycol)	< 5%
Transmission Fluid (Havoline Synthetic ATF)	< 5%
Engine Coolant (Havoline XLC, 50%/50% premixed)	< 5%
Diesel (Chevron #2)	< 5%
Gasoline (Chevron #91)	< 5%
Skydrol 500B-4	< 5%
<b>Strong Acid/Alcohol/Base</b>	
Sulfuric Acid (30%)	< 5%
Sodium Hydroxide (10%)	< 5%

**\*Percent weight gained after one week submersion following ASTM D543. Values do not represent changes in dimension or mechanical properties.**

## CE 221 UV Aging


Natural polymer aging can occur in the presence of light, sun, and heat. Carbon evaluated the UV aging performance of CE 221 using ASTM D4459, which is intended to simulate indoor exposure of solar radiation through glass.



ASTM 4459: Q-Sun XE-1, 0.8 W/m<sup>2</sup>/nm at 420 nm, 55 °C  
ASTM D638: Type V, 1 mm/min, average values represented

## CE 221 Dynamic Mechanical Analysis (DMA)

Dynamic mechanical analysis provides insight into the resin's viscoelastic properties across a range of temperatures. The figure below shows a temperature ramp of CE 221. This material exhibits a flat and high storage modulus up to a softening onset temperature of 190 °C, which reflects its rigid and temperature-resistant performance. The peak in the tan( $\delta$ ) curves indicates that the glass transition temperature of CE 221 is approximately 220 °C.



**Standard:** ASTM D4065

**Instrument:** TA DMA Q800

**DMA Mode:** Tension

**Sample Dimensions:** L=20 mm, W=10 mm, t=1 mm (rectangular block)

**Strain Amplitude:** 0.1% (linear regime of viscoelasticity)

**Oscillation frequency:** 1 Hz

**Temperature Range:** 0 °C to 250 °C

**Ramp Rate:** 1.5 °C/min

**Print Conditions:** Samples were hand-wiped and not washed with solvent. The thermal cure for all materials complies with the Carbon user manual. Values may differ based on post processing conditions.



# CE 221 Biocompatibility

## Biocompatibility Testing

Printed parts were provided to NAMSA for evaluation in accordance with ISO 10993-5, *Biological evaluation of medical devices - Part 5: Tests for in vitro cytotoxicity*. Parts were printed using an M series printer and washed in 50:50 (v:v) propylene glycol (PG) and isopropyl alcohol (IPA). The results indicated that CE 221 passed the requirements for biocompatibility according to the above test. **Carbon has not conducted ISO 10993-10, *Biological evaluation of medical devices - Part 10: Tests for irritation and skin sensitization (GPMT)* testing. Carbon makes no representation and is not responsible for the results of any biocompatibility tests other than those specified above.**

## Disclaimer

Biocompatibility results may vary based on printing and/or post-processing procedures.

Subscriber acknowledges the contents of this document are subject to the Terms and Conditions outlined in the Subscription Agreement, including the Restrictions on Use section.

DO NOT USE CARBON MATERIALS IN MEDICAL APPLICATIONS INVOLVING IMPLANTATION IN THE HUMAN BODY OR CONTACT WITH BODY FLUIDS OR TISSUES UNLESS THE MATERIAL HAS BEEN PROVIDED FROM CARBON UNDER A WRITTEN CONTRACT THAT IS CONSISTENT WITH THE CARBON POLICY REGARDING MEDICAL APPLICATIONS AND EXPRESSLY ACKNOWLEDGES THE CONTEMPLATED USE. CARBON MAKES NO REPRESENTATION, PROMISE, EXPRESS WARRANTY OR IMPLIED WARRANTY CONCERNING THE SUITABILITY OF THESE MATERIALS FOR USE IN IMPLANTATION IN THE HUMAN BODY OR IN CONTACT WITH BODY FLUIDS OR TISSUES. If Carbon has permitted in the Subscription Agreement use of the Carbon printer for applications that require biocompatibility, Subscriber acknowledges that it is the responsibility of Subscriber, its respective customers and end-users to determine the biocompatibility of all printed parts for their respective uses.

Carbon, Inc. | [www.carbon3d.com](http://www.carbon3d.com)  
1089 Mills Way Redwood City, CA 94063  
1 (650) 285-6307